

C&N is a professional manufacturer of steel forged flange .
 duplex stainless steel :A 182 Duplex F51 F53 F44 F55 F60
 Super Duplex UNS S32760 F55 Flange
 ASTM/ASME/ANSIB16.5, B16.47, ASME/ANSIB16.48 flange
 slip on flange, Weld Neck Flange ,Threaded Flange Blind Flange,
 Dimensions : ANSI Flanges, ASME Flanges, BS Flanges, DIN Flanges, EN Flanges etc.
 inquiry to bill@cnpipefitting.com

UNS S32760 A182 F55- Super Duplex Stainless Steel

Related Specifications

EN10088-3 X2CrNiMoCuWN25-7-4

ASTM A182 F55

W.Nr. 1.4501

NORSOK D51 to D55

F55 is a super duplex stainless steel with a 50:50 austenite, ferrite microstructure. The material combines high mechanical strength and good ductility with excellent corrosion resistance in a variety of environments. This material is generally supplied in the annealed condition giving yield strengths in excess of 80 KSI (550Mpa), this material cannot be hardened by heat treatment but stronger surface strengths can be achieved by cold working. This alloy is generally supplied with a Pitting Resistance Equivalent (PREn) of greater than 40 which guarantees high resistance to pitting corrosion. In addition high resistance to crevice and stress corrosion coupled with the increased strength give this alloy the advantage over the austenitic (300 series) and 22%Cr duplex stainless steels. Typical applications include many components for the chemical processing, marine, oil and gas, pollution control and food industries amongst others..

Typical Chemical composition

| | | |
|---|-------------|--------------|
| PREn = Pitting Resistance Equivalent PREn= Cr% + 3.3Mo% + 16N% | Carbon | 0.03% Max |
| | Silicon | 1.00% Max |
| | Manganese | 1.00% Max |
| | Phosphorous | 0.035% Max |
| | Sulphur | 0.015% Max |
| | Chromium | 24.0 - 26.0% |
| | Nickel | 6.0 - 8.0% |
| | Molybdenum | 3.0 - 4.0% |
| | Copper | 0.50 - 1.0% |
| | Nitrogen | 0.20 - 0.30% |
| | Tungsten | 0.50 - 1.0% |
| | PREn | >40 |

Mechanical Property Requirements - Annealed condition

| Yield | Tensile Strength | Elongation | Charpy Impact @ Rt J | Hardness |
|-----------------|--------------------------------|------------|-------------------------|-----------|
| >550Mpa (80KSI) | 730 - 930Mpa (106 - 135KSI) | 25% | 100 | 290HB Max |

Forging

Forging temperature for this material should be 1100 - 1250oC
 Reheat as often as necessary and cool in still air.

Heat Treatment

Anneal - Heat to 1100 - 1140oC ensuring sufficient time is allowed for the centre to achieve furnace temperature and hold for a time commensurate with the ruling section, followed by water quenching.

Machining

Material in the annealed condition is readily machinable by all conventional methods.

Welding

F55 is readily weldable using many of the standard electric arc welding processes but oxyacetylene welding is not recommended because carbon pickup in the weld metal may occur.