



# Standard Specification for UNS N06002, UNS N06230, UNS N12160, and UNS R30556 Plate, Sheet, and Strip<sup>1</sup>

This standard is issued under the fixed designation B 435; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification<sup>2</sup> covers alloys UNS N06002, UNS N06230, UNS N12160, and UNS R30556\* in the form of rolled plate, sheet, and strip for heat-resisting and general corrosive service.

1.2 The following products are covered under this specification:

1.2.1 *Sheet and Strip*—Hot- or cold-rolled, annealed, and descaled unless solution annealing is performed in an atmosphere yielding a bright finish.

1.2.2 *Plate*—Hot-rolled, solution-annealed, and descaled.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer; to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>3</sup>

**B 906** Specification for General Requirements for Flat-Rolled Nickel and Nickel Alloys Plate, Sheet, and Strip

**E 527** Practice for Numbering Metals and Alloys (UNS)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved June 1, 2006. Published June 2006. Originally approved in 1966. Last previous edition approved in 2003 as B 435 - 03.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications, see related Specification SB-435 in Section II of that Code.

\* New designation established in accordance with Practice **E 527** and SAE J1086, Practice for Numbering Metals and Alloys (UNS).

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *plate, n*—material  $\frac{3}{16}$  in. (4.76 mm) and over in thickness.

3.1.2 *sheet and strip, n*—material under  $\frac{3}{16}$  in. (4.76 mm) in thickness.

## 4. General Requirements

4.1 Material furnished under this specification shall conform to the applicable requirements of Specification **B 906** unless otherwise provided herein.

## 5. Ordering Information

5.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Examples of such requirements include, but are not limited to the following:

5.1.1 *Alloy*,

5.1.2 *Dimensions*—Thickness (in decimals of an inch), width, and length (inch or fraction of an inch),

5.1.3 *Certification*—State if certification or a report of test results is required (Specification **B 906**, section on Material Test Report and Certification),

5.1.4 *Optional Requirement*—Plate; state how plate is to be cut (Specification **B 906**, Table titled Permissible Variations in width and Length of Sheared, Torch-Cut, or Abrasive-Cut Rectangular Plate),

5.1.5 *Purchase Inspection*—State which tests or inspections are to be witnessed (Specification **B 906**, section on Inspection), and

5.1.6 *Samples for Product (Check) Analysis*—State whether samples should be furnished (Specification **B 906**, section on Sampling).

## 6. Chemical Composition

6.1 The material shall conform to the requirements as to chemical composition prescribed in **Table 1**.

6.2 If a product (check) analysis is made by the purchaser, the material shall conform to the requirements specified in **Table 1** and Specification **B 906**.

**TABLE 1 Chemical Requirements**

Element	Composition Limits, %			
	UNS N06002	UNS N06230	UNS R30556	UNS N12160
Nickel	remainder	remainder	19.0–22.5	remainder
Iron	17.0–20.0	3.0 max	remainder	3.5 max
Chromium	20.5–23.0	20.0–24.0	21.0–23.0	26.0–30.0
Cobalt	0.5–2.5	5.0 max	16.0–21.0	27.0–33.0
Molybdenum	8.0–10.0	1.0–3.00	2.5–4.0	1.0 max
Tungsten	0.2–1.0	13.0–15.0	2.0–3.5	1.0 max
Carbon	0.05–0.15	0.05–0.15	0.05–0.15	0.15 max
Silicon	1.00 max	0.25–0.75	0.20–0.80	2.4–3.0
Manganese	1.00 max	0.30–1.00	0.50–2.00	1.5 max
Phosphorus	0.04 max	0.030 max	0.04 max	0.030 max
Sulfur	0.03 max	0.015 max	0.015 max	0.015 max
Columbium (N6)	...	...	0.30 max	1.0 max
Tantalum	...	...	0.30–1.25	...
Aluminum	...	0.50 max	0.10–0.50	...
Zirconium	...	...	0.001–0.10	...
Lanthanum	...	0.005–0.050	0.005–0.10	...
Nitrogen	...	...	0.10–0.30	...
Boron	...	0.015 max	0.02 max	...
Titanium	...	...	...	0.20–0.80

## 7. Mechanical Properties and Other Requirements

7.1 *Tensile Properties*—The material shall conform to the room temperature tensile properties prescribed in [Table 2](#).

### 7.2 Grain Size for Sheet and Strip:

7.2.1 Annealed alloys UNS N06002, UNS N06230, and UNS R30556 sheet and strip shall conform to the grain size requirements given in [Table 3](#).

7.2.2 Annealed alloy UNS N12160 shall conform to an average grain size of ASTM No. 5 or coarser.

## 8. Dimensions, Mass, and Permissible Variations

8.1 *Weight*—For calculations of mass or weight, the following densities shall be used:

Alloy	Density lb/in. <sup>3</sup>	Density (g/cm <sup>3</sup> )
N06002	0.297	(8.23)
N06230	0.324	(8.97)
R30556	0.297	(8.23)
N12160	0.292	(8.08)

### 8.2 Thickness:

8.2.1 *Sheet and Strip*—The thickness shall be measured with the micrometer spindle  $\frac{3}{8}$  in. (9.525 mm) or more from any edge for material 1 in. (25.4 mm) or over in width and at any place on material under 1 in. in width.

### 8.3 Length:

8.3.1 *Sheet and Strip*—Sheet and strip may be ordered to cut lengths, in which case a variation of  $\frac{1}{8}$  in. (3.175 mm) over the specified length shall be permitted, with a 0 minus tolerance.

**TABLE 2 Mechanical Property Requirements**

UNS	Tensile Strength, min, ksi (MPa)	Yield Strength (0.2 % Offset), min, ksi (MPa)	Elongation in 2 in. (50.8 mm) or 4D, <sup>A</sup> min, %
N06002	95 (655)	35 (240)	35
N06230 <sup>B</sup>	110 (760)	45 (310)	40
R30556 <sup>C</sup>	100 (690)	45 (310)	40
N12160 <sup>D</sup>	90 (670)	35 (240)	40

<sup>A</sup> D refers to the diameter of the tension specimen.

<sup>B</sup> Solution annealed at a temperature between 2200 and 2275°F (1204 and 1246°C) followed by a water quench or rapidly cooled by other means.

<sup>C</sup> Solution annealed at 2100°F (1150°C) minimum.

<sup>D</sup> Solution annealed at 1950°F (1065°C) minimum.

**TABLE 3 Grain Size for Annealed Sheet**

Thickness, in. (mm)	ASTM Micrograin Size Number, max	Average Grain, Diameter, max, in. (mm)
0.125 (3.175) and under	3.0	0.0050 (0.127)
Over 0.125 (3.175)	1.5	0.0084 (0.214)

### 8.4 Straightness:

8.4.1 The edgewise curvature (depth of chord) of flat sheet, strip, and plate shall not exceed the product of 0.05 in. multiplied by the length in feet (0.04 mm multiplied by the length in centimetres).

8.4.2 Straightness for coiled strip is subject to agreement between the manufacturer and the purchaser.

8.5 *Squareness (Sheet)*—For sheets of all thicknesses and widths of 6 in. (152.4 mm) or more, the angle between adjacent sides shall be  $90 \pm 0.15^\circ$  ( $\frac{1}{16}$  in. in 24 in. or 2.6 mm/m).

8.6 *Flatness*—Plate, sheet, and strip shall be commercially flat.

### 8.7 Edges:

8.7.1 Plates shall have sheared, abrasive-cut or plasma-torch-cut edges as specified.

8.7.2 Sheet and strip shall have sheared or slit edges.

## 9. Product Marking

9.1 Each plate, sheet, or strip shall be marked on one face with the specification number, alloy, heat number, manufacturer's identification, and size. The markings shall have no deleterious effect on the material or its performance and shall be sufficiently stable to withstand normal handling.

9.2 Each bundle or shipping container shall be marked with the name of the material; this specification number; alloy; the size; gross, tare, and net weight; consignor and consignee address; contract or order number; and such other information as may be defined in the contract or order.

## 10. Keywords

10.1 plate; sheet; strip; UNS N06002; UNS N06230; UNS N12160; UNS R30556

**APPENDIX****(Nonmandatory Information)****X1. HEAT TREATMENT**

X1.1 Proper heat treatment during or subsequent to fabrication is necessary for optimum performance, and the manufacturer shall be consulted for details.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*