

SPECIFICATION FOR PRESSURE VESSEL PLATES, CARBON STEEL, MANGANESE-TITANIUM FOR GLASS OR DIFFUSED METALLIC COATINGS



SA-562/SA-562M



(Identical with ASTM Specification A562/A562M-10.)

Standard Specification for Pressure Vessel Plates, Carbon Steel, Manganese-Titanium for Glass or Diffused Metallic Coatings

1. Scope

1.1 This specification covers titanium-bearing carbon steel plates intended for welded glass lined pressure vessels or other applications where the presence of free-iron carbide would be deleterious to the coating. A minimum specific ratio of titanium to carbon is specified.

1.2 The maximum thickness of plates is limited to 2 in. [50 mm].

1.3 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

2. Referenced Documents

- 2.1 *ASTM Standards:*
A20/A20M Specification for General Requirements for Steel Plates for Pressure Vessels

3. General Requirements and Ordering Information

3.1 Material supplied to this material specification shall conform to Specification A20/A20M. These requirements outline the testing and retesting methods and procedures, permitted variations in dimensions, and mass, quality and repair of defects, marking, loading, and ordering information.

3.2 In addition to the basic requirements of this specification, certain supplementary requirements are available when additional control, testing, or examination is required to meet end use requirements.

3.3 If the requirements of this specification are in conflict with the requirements of Specification A20/A20M, the requirements of this specification shall prevail.

4. Manufacture

- 4.1 *Steelmaking Practice*—The steel shall be killed.

5. Heat Treatment

5.1 Plates shall be thermally treated to produce grain refinement, either by normalizing or heating uniformly for hot forming at a minimum temperature of 1600°F [870°C] or some higher agreed temperature, and held at this temperature for a minimum of 1 h/in. [2.4 min/mm] of thickness.

6. Chemical Requirements

6.1 The steel shall conform to the chemical requirements shown in Table 1 unless otherwise modified in accordance with Supplementary Requirement S17, Vacuum Carbon-Deoxidized Steel, in Specification A20/A20M.

7. Mechanical Requirements

7.1 *Tension Test Requirements*—The material as represented by the tension-test specimens shall conform to the requirements shown in Table 2.

TABLE 1 Chemical Requirements

Element	Composition, %
Carbon, max ^A	0.12
Manganese, max	
Heat analysis	1.20
Product analysis	1.30
Phosphorus, max ^A	0.025
Sulfur, max ^A	0.025
Silicon ^A	0.15–0.50
Copper, max ^A	0.15
Titanium, min	4 × C

^A Applies to both heat and product analyses.

TABLE 2 Tensile Requirements

	ksi [MPa]
Tensile strength	55–75 [380–515]
Yield strength, min	30 [205]
Elongation in 8 in. [200 mm] min, % ^A	22
Elongation in 2 in. [50 mm] min, % ^A	26

^A See Specification A20/A20M for elongation adjustments.

SUPPLEMENTARY REQUIREMENTS

Supplementary requirements shall not apply unless specified in the order.

A list of standardized supplementary requirements for use at the option of the purchaser are included in Specification A20/A20M. Those which are considered suitable for use with this specification are listed below by title.

- | | |
|---|---|
| <ul style="list-style-type: none"> S1. Vacuum Treatment, S2. Product Analysis, S3. Simulated Post-Weld Heat Treatment of Mechanical Test Coupons, S4. Additional Tension Test, S5. Charpy V-Notch Impact Test, S6. Drop Weight Test (for Material 0.625 in. [16 mm] and over in Thickness), S7. High-temperature Tension Test, | <ul style="list-style-type: none"> S8. Ultrasonic Examination in accordance with Specification A435/A435M, S9. Magnetic Particle Examination, S11. Ultrasonic Examination in accordance with Specification A577/A577M, S12. Ultrasonic Examination in accordance with Specification A578/A578M, and S17. Vacuum Carbon-Deoxidized Steel. |
|---|---|

INTENTIONALLY LEFT BLANK